

**HEDVA a.s.**  
Moravská Třebová  
fax:00420 461 356 409

**T E C H N I C A L   D A T A**

material designation : **R I D A N A / L** width :140/136cm  
finishing : dyeing RUCOFLAM weave : twill  
recommended use : **polyamide technical fabrics**

yarn warp : polyamid  
weft : polyamid

sett 10 cm warp : 425 CSN EN 1049-2  
weft : 210

weight g/sq.m : 210 inform. CSN EN 12127

strenght mind.(arith.mean) N warp : 1800 CSN EN ISO 13934-1  
weft : 1300

resistance to shifting N mind. : -  
fire-retardent deg. mind. : B1 DIN 4102-1  
air - permeability liter/sq m.sec. : - CSN EN ISO 9237  
water-proof cm W-culumn mind. : - CSN EN 20811  
washing shrinkage 40°C %max.warp : 2 PNs47451963/020/  
weft : 2 80/97  
oleophobite deg. mind. : - test AATCC - 118  
Spraytest deg. mind. : - CSN EN 24920  
composition % : 100 polyamid

---

light colour fastness mind.: 4 CSN EN ISO 105-B02  
fastness to dry cleaning mind.: - CSN EN ISO 105-D01  
dry rubbing fastnees mind.: 4 - 5 CSN EN ISO 105-X12  
fastness to dry ironing mind.: 4 - 5/4 - 5 CSN EN ISO 105-X11  
wash fastness 40° C mind.: - CSN EN ISO 105-C10  
perspiration fastness mind.: 4 - 5/4 - 5 CSN EN ISO 105-E04

re.dark colour shades and black colour fastness can be 0,5 up to 1,0 lower,  
this does not concern fastnessto light

treatment symbols :  CSN EN ISO 3758

14.5.2012

**HEDVA**, akciová společnost  
**MORAVSKÁ TŘEBOVÁ**  
PSČ 571 21

ing.Věra Šušarová